

6FM60GD-X 12V 60Ah(20h)

The rechargeable batteries are lead-lead dioxide systems. The dilute sulfuric acid electrolyte is absorbed by separators and plates and thus immobilized. Should the battery be accidentally overcharged producing hydrogen and oxygen, special one-way valves allow the gases to escape thus avoiding excessive pressure build-up. Otherwise, the battery is completely sealed and is, therefore, maintenance-free, leak proof and usable in any position.

Battery Construction

Component	Positive plate	Negative plate	Container	Cover	Safety valve	Terminal	Separator	Electrolyte
Raw material	Lead dioxide	Lead	ABS	ABS	Rubber	Pb	Fiberglass	Sulfuric acid

General Features

- Gel and Absorbent Glass Mat (AGM) technology for efficient gas recombination of up to 99% and freedom from electrolyte maintenance or water adding.
- Not restricted for air transport-complies with IATA/ICAO Special Provision A67.
- UL-recognized component.
- Can be mounted in any orientation.
- Computer designed lead, calcium tin alloy grid for high power density.
- Long service life, float or cyclic applications.
- Maintenance-free operation.
- Low self discharge.


Performance Characteristics

Nominal Voltage	12V
Number of cell	6
Design Life	10 years
Nominal Capacity 77°F(25°C)	
20 hour rate (3.00A, 10.8V)	60Ah
10 hour rate (5.87A, 10.8V)	58.7Ah
5 hour rate (10.6A, 10.5V)	53.0Ah
1 hour rate (40.4A, 9.6V)	40.4Ah
Internal Resistance	
Fully Charged battery 77°F(25°C)	≤ 7.0mOhms
Self-Discharge	
3% of capacity declined per month at 20°C(average)	
Operating Temperature Range	
Discharge	-20~60°C
Charge	-10~60°C
Storage	-20~60°C
Max. Discharge Current 77°F(25°C)	600A(5s)
Short Circuit Current	1450A
Charge Methods: Constant Voltage Charge 77°F(25°C)	
Cycle use	2.40-2.45VPC
Maximum charging current	18A
Temperature compensation	-30mV/°C
Temperature compensation	-20mV/°C

Dimensions and Weight

Length(mm / inch)	258 / 10.16
Width(mm / inch)	166 / 6.54
Height(mm / inch)	206 / 8.11
Total Height(mm / inch)	215 / 8.46
Approx. Weight(Kg / lbs)	24 / 52.9

* Weight deviation: ± 3%



Discharge Constant Current (Amperes at 77°F25°C)


End Point Volts/Cell	10min	15min	30min	45min	1h	3h	5h	10h	20h
1.60V	143	112	65.4	49.3	40.4	16.5	11.3	5.98	3.08
1.65V	138	107	63.4	47.9	38.8	16.1	11.0	5.96	3.06
1.70V	128	102	61.5	46.7	38.6	16.1	10.8	5.93	3.04
1.75V	118	96.5	59.4	45.3	38.3	15.8	10.6	5.90	3.02
1.80V	108	89.3	57.3	44.0	36.1	15.0	10.4	5.87	3.00

Discharge Constant Power (Watts at 77°F25°C)


End Point Volts/Cell	10min	15min	30min	45min	1h	2h	3h	5h
1.60V	249	194	119	92.3	76.5	43.9	32.7	22.1
1.65V	238	184	113	90.8	74.7	43.0	32.5	22.0
1.70V	225	182	111	88.9	73.0	42.1	31.8	21.6
1.75V	212	178	109	87.0	71.3	41.2	31.1	21.3
1.80V	197	169	106	86.2	70.0	40.3	30.4	20.7

(Note)The above characteristics data are average values obtained within three charge/discharge cycles not the minimum values. All data shall be changed without notice,Luxury reserves the right to explain and update the information contained hereinto.


Life characteristics of standby use




Cycle service life in relation to depth of discharge




Relationship of OCV and state of charge (25°C)



Self-discharge characteristic



Temperature effects on float life



Temperature effects on capacity

