

# CP1290A 12V9Ah

The rechargeable batteries are lead-lead dioxide systems. The dilute sulfuric acid electrolyte is absorbed by separators and plates and thus immobilized. Should the battery be accidentally overcharged producing hydrogen and oxygen, special one-way valves allow the gases to escape thus avoiding excessive pressure build-up. Otherwise, the battery is completely sealed and is, therefore, maintenance-free, leak proof and usable in any position.


#### Construction


Component	Positive plate	Negative plate	Container	Cover	Safety valve	Terminal	Separator	Electrolyte
Raw material	Lead dioxide	Lead	ABS	ABS	Rubber	Copper	Fiberglass	Sulfuric acid

#### **General Features**

- Absorbent Glass Mat (AGM) technology for efficient gas recombination of up to 99% and freedom from electrolyte maintenance or water adding.
- Not restricted for air transport-complies with IATA/ICAO Special Provision A67.
- UL-recognized component.
- Can be mounted in any orientation.
- Computer designed lead, calcium tin alloy grid for high power density.
- Long service life, float or cyclic applications.
- Maintenance-free operation.
- Low self discharge.
- Case and cover available in both standard and flame retardant ABS.

### **Dimensions and Weight**





terminal F2

# **Technology Parameter**

Battery model	CP1290A							
ominal voltage	12V							
Number of cell	6							
Capacity	20hR(0.45A, 10.5V)	10hR(0.86A, 10.5V)		5hR(1.57A, 10.5V)		1hR(6.66A, 9.60V)		
(25℃)	9Ah 8.6Ah		7.85Ah		6.66Ah			
Dimensions	Length	Width		Height		Total Height		
Dimensions	151±1mm	65±1mm		94±1mm		100±1mm		
Approx. weight	2.78Kg (6.13 lbs)							
Internal resistance	Full charged at $25^\circ C$ : $\leqslant$ 12.5 mOhms							
Self discharge	3% of cap	% of capacity declined per month at 20 $^\circ\!\!\mathbb{C}$ (average)						
Operating	Discharge	е	Charge			Storage		
temperature range	<b>-20∼60°</b> ℃		-10∼60°C		<b>-20∼60°</b> ℃			
Max. discharge current (25℃)	135A (5s)							
Short circuit current	450A							

## Discharge Constant Current (Amperes at 77°F25°C)

End Point Volts/Cell	5min	10min	15min	30min	1h	3h	5h	10h	20h
1.60V	36.1	25.2	19.3	11.6	6.66	2.59	1.62	0.88	0.47
1.65V	34.6	24.3	18.5	11.1	6.42	2.53	1.61	0.87	0.47
1.70V	33.1	23.3	17.7	10.5	6.18	2.46	1.59	0.87	0.46
1.75V	31.6	22.2	16.9	9.86	5.94	2.39	1.57	0.86	0.45
1.80V	30	21.2	16.1	9.21	5.68	2.32	1.55	0.85	0.44

# Discharge Constant Power (Watts at 77°F25°C)

End Point Volts/Cell	5min	10min	15min	30min	45min	1h	2h	Зh	5h
1.60V	74.1	47.2	35.1	21.5	15.9	12.4	6.85	4.84	3.27
1.65V	70.5	45.6	34	20.8	15.3	12	6.72	4.79	3.24
1.70V	66.9	43.9	32.9	20.0	14.7	11.5	6.59	4.74	3.21
1.75V	63.3	42.2	31.8	19.2	14.1	11	6.46	4.69	3.18
1.80V	59.7	40.5	30.7	18.4	13.5	10.5	6.32	4.64	3.15


(Note)The above characteristics data are average values obtained within three charge/discharge cycles not the mimimum values.


All data shall be changed without notice, LUXURY reserves the right to explain and update the information contained hereinto.


http://www.luxury-system.com













E-mail: sales@luxury-system.com Website: http://www.luxury-system.com

